

Tested: NFRC-2004

Qualify : 0.30 SHGC / 0.30 U-factor

Product Model	Struct. Performance			Glazing Options					Thermal Performance				Condensation Resistance
	Air Leakage	Water Leakage	Wind Load	Spacer	Layers	Low E. Type	Low E.	Gas	R - Value (Imperial)	Visual Transmit.	U-Factor (Imperial)	SHGC	
210C	A3	B7	C3	Stainless	2	Hard coat	Surface 3	Argon	R 3.03	0.58	0.33	0.55	56
210C	A3	B7	C3	Stainless	2	Soft Coat	Surface 2	Argon	R 3.45	0.55	0.29	0.3	60
210C	A3	B7	C3	Stainless	3	Hard coat	Surface 5	Argon	R 3.23	0.53	0.31	0.48	58
210C	A3	B7	C3	Stainless	3	Soft Coat	Surface 2&5	Argon	R 4.16	0.44	0.24	0.26	66
300	A2	B3	C3	Stainless	2	Hard coat	Surface 3	Argon	R 2.94	0.56	0.34	0.54	55
300	A2	B3	C3	Stainless	2	Soft Coat	Surface 2	Argon	R 3.45	0.54	0.29	0.29	59
300	A2	B3	C3	Stainless	3	Hard coat	Surface 5	Argon	R 3.23	0.52	0.31	0.47	58
300	A2	B3	C3	Stainless	3	Soft Coat	Surface 2&5	Argon	R 4	0.43	0.25	0.25	65
100M	A3	B7	C5	Stainless	2	Hard Coat	Surface 3	Argon	R 3.23	0.50	0.31	0.49	59
100M	A3	B7	C5	Stainless	2	Soft Coat	Surface 2	Argon	R 3.57	0.48	0.28	0.26	62
100M	A3	B7	C5	Stainless	3	Hard Coat	Surface 5	Argon	R 4	0.46	0.25	0.43	68
100M	A3	B7	C5	Stainless	3	Soft Coat	Surface 2 & 5	Argon	R 5.26	0.39	0.19	0.23	75
150M	A3	B7	C4	Stainless	2	Hard Coat	Surface 3	Argon	R 3.23	0.50	0.31	0.49	56
150M	A3	B7	C4	Stainless	2	Soft Coat	Surface 2	Argon	R 3.57	0.48	0.28	0.26	58
150M	A3	B7	C4	Stainless	3	Hard Coat	Surface 5	Argon	R 4.16	0.46	0.24	0.43	67
150M	A3	B7	C4	Stainless	3	Soft Coat	Surface 2 & 5	Argon	R 5.55	0.39	0.18	0.23	76
452	FX	B7	C5	Stainless	2	Hard Coat	Surface 3	Argon	R 3.125	0.59	0.32	0.56	57
452	FX	B7	C5	Stainless	2	Soft Coat	Surface 2	Argon	R 3.7	0.56	0.27	0.30	61
452	FX	B7	C5	Stainless	3	Hard Coat	Surface 5	Argon	R 4.16	0.54	0.24	0.50	67
452	FX	B7	C5	Stainless	3	Soft Coat	Surface 2 & 5	Argon	R 6.25	0.45	0.16	0.26	75
402	FX	B7	C5	Stainless	2	Hard Coat	Surface 3	Argon	R 3.23	0.66	0.31	0.63	59
402	FX	B7	C5	Stainless	2	Soft CoatSB60	Surface 2	Argon	R 3.7	0.64	0.27	0.34	62
402	FX	B7	C5	Stainless	2	Soft CoatSB70	Surface 2	Argon	R 3.85	0.57	0.26	0.24	63
402	FX	B7	C5	Stainless	3	Hard Coat	Surface 5	Argon	R 4.35	0.60	0.23	0.56	69
201	A3	B3	C3	Stainless	2	Hard Coat	Surface 3	Argon	R 3.03	0.59	0.33	0.56	55
201	A3	B3	C3	Stainless	2	Soft Coat	Surface 2	Argon	R 3.57	0.56	0.28	0.30	59
201	A3	B3	C3	Stainless	3	Hard Coat	Surface 5	Argon	R 3.23	0.54	0.31	0.49	58
201	A3	B3	C3	Stainless	3	Soft Coat	Surface 2 & 5	Argon	R 4.35	0.45	0.23	0.26	66
301	A3	B2	C3	Stainless	2	Hard Coat	Surface 3	Argon	R 3.03	0.59	0.33	0.56	56
301	A3	B2	C3	Stainless	2	Soft Coat	Surface 2	Argon	R 3.57	0.56	0.28	0.30	60
301	A3	B2	C3	Stainless	3	Hard Coat	Surface 5	Argon	R 3.23	0.54	0.31	0.49	58
301	A3	B2	C3	Stainless	3	Soft Coat	Surface 2 & 5	Argon	R 4.35	0.45	0.23	0.26	65
240	A3	B7	C3	Stainless	2	Hard Coat	Surface 3	Argon	R 2.94	0.59	0.34	0.56	53
240	A3	B7	C3	Stainless	2	Soft Coat	Surface 2	Argon	R 3.45	0.56	0.29	0.30	57
340	A3	B3	C4	Stainless	2	Hard Coat	Surface 3	Argon	R 2.94	0.58	0.34	0.55	54
340	A3	B3	C4	Stainless	2	Soft Coat	Surface 2	Argon	R 3.45	0.56	0.29	0.30	57
355	A2	B2	C2	Stainless	2	Hard Coat	Surface 3	Argon	R 2.86	0.59	0.35	0.56	55
355	A2	B2	C2	Stainless	2	Soft Coat	Surface 2	Argon	R 3.33	0.56	0.3	0.3	58
275	A2	B2	C2	Stainless	2	Hard Coat	Surface 3	Argon	R 2.94	0.61	0.34	0.58	55
275	A2	B2	C2	Stainless	2	Soft Coat	Surface 2	Argon	R 3.57	0.58	0.28	0.31	59
375	A2	B2	C2	Stainless	2	Hard Coat	Surface 3	Argon	R 2.94	0.61	0.34	0.58	55
375	A2	B2	C2	Stainless	2	Soft Coat	Surface 2	Argon	R 3.45	0.58	0.29	0.31	59